

Last updated: 04/07/2024 06:26:49

TIMM MASTER 12 SBA 80MM 220M 1231KN (SPLICED)/1368KN (UNSPLICED) WHITE/BLUE 2X1,8M EYE

Product group: 320 Product number: L142896

Product information

Timm Master 12 SBA is a mixed polymer rope solution, using the

Features

- 12 strand plaited construction
- Anti-twisting colors
- Integrated Snap Back Arrestor
- Buoyant
- Low-torque
- UV stabilised

Benefits

- Reducing snap back if main rope breaks
- Class leading strength-to-weight ratio
- Preventing twisting of ropes
- High abrasion resistance
- Type Approved by DNV GL
- Meets all OCIMF requirements

Specification

General

Invent Hazard Material (IMO/EU) classification	NA
Material	75% Polyolefin & 25% HT Polyester
Material type and grade	Mixed polyolefins (B5 yarn) and HT PES

Physical properties

Colour	Blue and white anti-twisting colors
Construction	12 strand braided
Density	0.99
Density [kg/m3]	0.99
Elongation [%]	18% at break
Eyes	1,8mmesh braid protected eyes
Jacketed	false
Line Construction	12x1 braided
Line Tenacity (LT) Maximum	38.41 t/kg/m
Line Tenacity (LT) Maximum (kNg/m)	0.38 kNg/m
Melting point	165°C
NSBF (if requested)	Nbt requested
Rotating	false
Splice type and design	TM12 2G
X - Line Tenacity (LT) Maximum	38.41 t/kg/m
X - Line Tenacity (LT) Maximum (kNg/m)	0.38 kNg/m
X - Splice type and design	TM12 2G

Dimensions/Weight

Diameter [mm]	80
Length	220
Length [m]	220

Technical data

Angled Break Force (ABF) % Avg NSBF D/d = 10	181.42 (90.71)
Angled Break Force (ABF) % Avg NSBF D/d = 5	173.00 (86.50)
Angled Endurance (AE) % Avg NSBF D/d = 10	78.21
Angled Endurance (AE) % Avg NSBF D/d = 5	75.13
Average Immediate Strain (e) %LDBF:10	1.33
Average Immediate Strain (e) %LDBF:20	2.50
Average Immediate Strain (e) %LDBF:30	3.50
Average Immediate Strain (e) %LDBF:40	4.36
Average Immediate Strain (e) %LDBF:50	5.24
Axial Compression Resistance (ACR)	94.53% Avg NSBF
Temperature (T) % BF at 20°C -20C	135/101
Temperature (T) % BF at 20°C 0C	124/103
Temperature (T) % BF at 20°C 20C	100/100
Temperature (T) % BF at 20°C 40C	84/93
Temperature (T) % BF at 20°C 60C	72/89
Temperature (T) % BF at 20°C 80C	57/89
Water absorption [%]	<1%
X - Angled Break Force (ABF) % Avg NSBF D/d = 10	181.42 (90.71)
X - Angled Break Force (ABF) % Avg NSBF D/d = 5	173.00 (86.50)
X - Angled Endurance (AE) % Avg NSBF D/d = 10	78.21
X - Angled Endurance (AE) % Avg NSBF D/d = 5	75.13
X - Average Immediate Strain (e) %LDBF:10	1.33
X - Average Immediate Strain (e) %LDBF:20	2.50
X - Average Immediate Strain (e) %LDBF:30	3.50
X - Average Immediate Strain (e) %LDBF:40	4.36
X - Average Immediate Strain (e) %LDBF:50	5.24
X - Axial Compression Resistance (ACR)	94.53% Avg NSBF
X - Temperature (T) % BF at 20°C -20C	135/101
X - Temperature (T) % BF at 20°C 0C	124/103
X - Temperature (T) % BF at 20°C 20C	100/100
X - Temperature (T) % BF at 20°C 40C	84/93
X - Temperature (T) % BF at 20°C 60C	72/89
X - Temperature (T) % BF at 20°C 80C	57/89

X - Temperature (T) %BF at 20°C 60C	12/89
X - Temperature (T) %BF at 20°C 80C	57/89

Performance data

DNVGL	Y
SBA	Y
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

Approvals

Snapback arrestor is a Verifed Product by DNV GL.
Timm Master 12 is Type Approved by DNV GL. This product is produced according to ISO 9554 and tested according to ISO 2307. Minimum Breaking Load (MBL) is according to
ISO 10556 and verified by DNV GL.

Manufactured acc. to => ISO 9554, ISO 10556
Tested acc. to => ISO 2307, CI 1500A, DNVGL-CP-0100
Type Approval No => TAK0000094
X- Type Approval No => TAK0000094

Documents

Use and Care Timm Master 12 SBA

This page is printed from
<https://www.wilhelmsen.com/product-catalogue/products/ropes/conventional-mooring-ropes/timm-master-12-sba/timm-master-12-sba-80mm-220m-1231kn-spliced1368kn-unspliced-whiteblue-2x18m-eye>