

Last updated: 08/08/2024 06:47:33

# TIMM MASTER 12 SBA F80 [67MM] 180M

Product group: **327**    Product number: **411239**



## Product information

Timm Master 12 SBA is a mixed polymer rope solution, using the

### Features

- 12 strand plaited construction
- Anti-twisting colors
- Integrated Snap Back Arrestor
- Buoyant
- Low-torque
- UV stabilised

### Benefits

- Reducing snap back if main rope breaks
- Class leading strength-to-weight ratio
- Preventing twisting of ropes
- High abrasion resistance
- Type Approved by DNV GL
- Meets all OCIMF requirements

## Specification

## General

<b>Invent Hazard Material (IMO/EU) classification</b>	NA
<b>Material</b>	75% Polyolefin & 25% HT Polyester
<b>Material type and grade</b>	Mxed polyolefins (B5 yarn) and HT PES

## Dimensions/Weight

<b>Diameter [mm]</b>	67
<b>Length</b>	180
<b>Length [m]</b>	180

## Performance data

<b>DNVGL</b>	Y
<b>SBA</b>	Y
<b>Strength adjustment</b>	10%
<b>Var Range From</b>	100%
<b>Var Range To</b>	105%

## Physical properties

<b>Colour</b>	Blue and white anti-twisting colors
<b>Construction</b>	12 strand braided
<b>Density</b>	0.99
<b>Density [kg/m<sup>3</sup>]</b>	0.99
<b>Elongation [%]</b>	18% at break
<b>Eyes</b>	1,8mm mesh braid protected eyes
<b>Jacketed</b>	false
<b>Line Construction</b>	12x1 braided
<b>Line Linear Density (LLD)</b>	2.43 kg/m
<b>Line Tenacity (LT) Maximum</b>	38.41 t/kg/m
<b>Line Tenacity (LT) Maximum (kN/m)</b>	0.38 kN/m
<b>Line Tenacity (LT) Measured</b>	37.81 t/kg/m
<b>Load Bearing Linear Density (LBLD)</b>	2.341 kg/m
<b>Melting point</b>	165°C
<b>NSBF (if requested)</b>	Not requested
<b>Rotating</b>	false
<b>Splice type and design</b>	TM12 2G

## Technical data

<b>Angled Break Force (ABF) % Avg NSBF D/d = 10</b>	192.22 (96.10)
<b>Angled Break Force (ABF) % Avg NSBF D/d = 5</b>	195.17 (97.58)
<b>Angled Endurance (AE) % Avg NSBF D/d = 10</b>	68.07
<b>Angled Endurance (AE) % Avg NSBF D/d = 5</b>	79.81
<b>Average Immediate Strain (e) %LDBF:10</b>	1.06
<b>Average Immediate Strain (e) %LDBF:20</b>	2.37
<b>Average Immediate Strain (e) %LDBF:30</b>	3.55
<b>Average Immediate Strain (e) %LDBF:40</b>	4.66
<b>Average Immediate Strain (e) %LDBF:50</b>	5.72
<b>Axial Compression Resistance (ACR)</b>	102.5% Avg NSBF
<b>LDBF [kN] (from)</b>	747
<b>LDBF [kN] (up to)</b>	869
<b>LDBF [t] (from)</b>	76.0
<b>LDBF [t] (up to)</b>	88.5
<b>Line Design Break Force (LDBF)</b>	88.5
<b>Temperature (T) % BF at 20°C -20C</b>	107.6/109/115
<b>Temperature (T) % BF at 20°C 0C</b>	108.5/109/105
<b>Temperature (T) % BF at 20°C 20C</b>	100/100/100
<b>Temperature (T) % BF at 20°C 40C</b>	89.3/98/95
<b>Temperature (T) % BF at 20°C 60C</b>	77.5/92/90
<b>Temperature (T) % BF at 20°C 80C</b>	55/88/82
<b>Unspliced MBL [t]</b>	98.4

## Approvals

Snapback arrestor is a Verified Product by DNV GL.

Timm Master 12 is Type Approved by DNV GL. This product is produced according to ISO 9554 and tested according to ISO 2307. Minimum Breaking Load (MBL) is according to

ISO 10556 and verified by DNV GL.

Manufactured acc. to => ISO 9554, ISO 10556

Tested acc. to => ISO 2307, CI 1500A, DNVGL-CP-0100

Type Approval No => TAK0000094

## Documents

[Wilhelmsen Use and Care Timm Master 12 SBA](#)

This page is printed from

<https://www.wilhelmsen.com/product-catalogue/products/ropes/conventional-mooring-ropes/timm-master-12-sba/timm-master-12-sba-f80-67mm-180m3/>