

Last updated: 04/07/2024 06:26:52

## TIMM MASTER 8 40MM 220M WHITE 2X1,8M EYE

Product group: **320** Product number: **410051**

Timm Master 8 is one of the most selling premium mixed polymer ropes. A reliable, flexible, and tough mooring rope suitable for all ship types.



### Product information

Our most recognised product to date, long admired as a premium, mixed polymer rope solution. We have sold Timm Master to over 6,000 vessels worldwide. Our Master ropes are supplying a significant proportion of the world's largest shipping companies. This is a flexible and easily handled product made from our Timm Signal B5 polyolefin yarn and high tenacity polyester and has long been admired as a premium, mixed polymer mooring rope. Master ropes have a low cost of ownership, very good abrasion properties and excellent UV resistance. The product is buoyant (<1% water absorption) and 18% elongation at break.

#### Features

- 8-strand plaited construction
- Buoyant
- Low-torque
- UV stabilised

#### Benefits

- Class leading strength-to-weight ratio
- High abrasion resistance
- Type approval from DNV GL
- Meets all OCIMF requirements
- Held in global stock inventory

### Specification

General

<b>Invent Hazard Material (IMO/EU) classification</b>	NA
<b>Material</b>	Mixed polyolefins (B5 yarn) and HT PES
<b>Material type and grade</b>	Mixed polyolefins (B5 yarn) and HT PES

Physical properties

<b>Colour</b>	White with 3 black marking yarns
<b>Construction</b>	8-strand plaited rope
<b>Density</b>	0.99
<b>Density [kg/m<sup>3</sup>]</b>	0.99
<b>Elongation [%]</b>	18% at break
<b>Eyes</b>	1.8m protected eyes (PES)
<b>Jacketed</b>	false
<b>Line Construction</b>	8-strand braided
<b>Line Linear Density (LLD)</b>	0.84 kg/m
<b>Line Tenacity (LT) Maximum</b>	38.41 t/kg/m
<b>Line Tenacity (LT) Maximum (kN/g/m)</b>	0.38 kN/g/m
<b>Line Tenacity (LT) Measured</b>	38.12 t/kg/m
<b>Load Bearing Linear Density (LBLD)</b>	0.84 kg/m
<b>Melting point</b>	165°C
<b>NSBF (if requested)</b>	Not requested
<b>Rotating</b>	false
<b>Splice type and design</b>	Tuck (4S-4Z)x5
<b>X - Line Linear Density (LLD)</b>	0.84 kg/m
<b>X - Line Tenacity (LT) Maximum</b>	38.41 t/kg/m
<b>X - Line Tenacity (LT) Maximum (kN/g/m)</b>	0.38 kN/g/m
<b>X - Line Tenacity (LT) Measured</b>	38.12 t/kg/m
<b>X - Load Bearing Linear Density (LBLD)</b>	0.84 kg/m
<b>X - Splice type and design</b>	Tuck (4S-4Z)x5

Dimensions/Weight

<b>Diameter [mm]</b>	40
<b>Length</b>	220
<b>Length [m]</b>	220

Technical data

<b>Angled Break Force (ABF) % Avg NSBF D/d = 10</b>	181.42 (90.71)
<b>Angled Break Force (ABF) % Avg NSBF D/d = 5</b>	173.00 (86.50)
<b>Angled Endurance (AE) % Avg NSBF D/d = 10</b>	78.21
<b>Angled Endurance (AE) % Avg NSBF D/d = 5</b>	75.13
<b>Average Immediate Strain (e) %LDBF:10</b>	1.33
<b>Average Immediate Strain (e) %LDBF:20</b>	2.50
<b>Average Immediate Strain (e) %LDBF:30</b>	3.50
<b>Average Immediate Strain (e) %LDBF:40</b>	4.36
<b>Average Immediate Strain (e) %LDBF:50</b>	5.24
<b>Axial Compression Resistance (ACR)</b>	94.53% Avg NSBF
<b>Line Design Break Force (LDBF)</b>	32.1
<b>Spliced MBL/LDBF [kN]</b>	315
<b>Temperature (T) % BF at 20°C -20C</b>	135/101
<b>Temperature (T) % BF at 20°C 0C</b>	124/103
<b>Temperature (T) % BF at 20°C 20C</b>	100/100
<b>Temperature (T) % BF at 20°C 40C</b>	84/93
<b>Temperature (T) % BF at 20°C 60C</b>	72/89
<b>Temperature (T) % BF at 20°C 80C</b>	57/89
<b>Unspliced MBL [kN]</b>	350
<b>Unspliced MBL [t]</b>	35.7
<b>Water absorption [%]</b>	<1%
<b>X - Angled Break Force (ABF) % Avg NSBF D/d = 10</b>	181.42 (90.71)
<b>X - Angled Break Force (ABF) % Avg NSBF D/d = 5</b>	173.00 (86.50)
<b>X - Angled Endurance (AE) % Avg NSBF D/d = 10</b>	78.21
<b>X - Angled Endurance (AE) % Avg NSBF D/d = 5</b>	75.13

X - Average Immediate Strain (e) %\LDBF:10	1.33
X - Average Immediate Strain (e) %\LDBF:20	2.50
X - Average Immediate Strain (e) %\LDBF:30	3.50
X - Average Immediate Strain (e) %\LDBF:40	4.36
X - Average Immediate Strain (e) %\LDBF:50	5.24
X - Axial Compression Resistance (ACR)	94.53% Avg NSBF
X - Line Design Break Force (LDBF)	32.1
X - Spliced MBL/LDBF [kN]	315
X - Temperature (T) % BF at 20°C -20C	135/101
X - Temperature (T) % BF at 20°C 0C	124/103
X - Temperature (T) % BF at 20°C 20C	100/100
X - Temperature (T) % BF at 20°C 40C	84/93
X - Temperature (T) % BF at 20°C 60C	72/89
X - Temperature (T) % BF at 20°C 80C	57/89
X - Unspliced MBL [t]	35.7

#### Performance data

DNVGL	Y
SBA	N
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

## Approvals

Type Approved Product by DNV GL. This product is produced according to ISO 9554 and tested according to ISO 2307. Minimum Breaking Load (MBL) is according to ISO 10556 and verified by DNV GL.

Manufactured acc. to => ISO 9554, ISO 10556

Tested acc. to => ISO 2307, CI 1500A, DNVGL-CP-0100

Type Approval No => TAK0000094

X- Type Approval No => TAK0000094

[TAK0000094](#)

## Documents

[Wilhelmsen Use and Care Timm Master 8](#)

[SDoC and MD for IHM](#)

## Related products

Is frequently bought together with

**743146**

GAMAZYME TDS 5 KG BLUE SACH W/MINT

**410167**

TIMMMASTER 8 TAIL 76MM 11M WHITE 2X2,0MEYE

**410095**

TIMMMASTER 8 64MM 220M WHITE 2X1,8MEYE

**410099**

TIMMMASTER 8 68MM 220M WHITE 2X1,8MEYE

This page is printed from

<https://www.wilhelmsen.com/product-catalogue/products/ropes/conventional-mooring-ropes/timm-master-8/timm-master-8-40mm-220m-315kn-spliced350kn-unspliced-white-2x18m-eye>