

Last updated: 08/08/2024 06:47:34

TIMM MASTER 8 44MM 220M WHITE 2X1,8M EYE

Product group: 320 Product number: 410055

Timm Master 8 is one of the most selling premium mixed polymer ropes. A reliable, flexible, and tough mooring rope suitable for all ship types.

2020 BOR

Product information

Our most recognised product to date, long admired as a premium, mixed polymer rope solution. We have sold Timm Master to over 6,000 vessels worldwide. Our Master ropes are supplying a significant proportion of the world's largest shipping companies. This is a flexible and easily handled product made from our Timm Signal B5 polyolefin yarn and high tenacity polyester and has long been admired as a premium, mixed polymer mooring rope. Master ropes have a low cost of ownership, very good abrasion properties and excellent UV resistance. The product is buoyant (<1% water absorption) and 18% elongation at break.

Features

- 8-strand plaited construction
- Buoyant
- Low-torque
- UVstabilised

Benefits

- Class leading strength-to-weight ratio
- High abrasion resistance
- Type approval from DNV GL
- Meets all OCIMF requirements
- Held in global stock inventory

Specification

General

Invent Hazard Material (IMO/EU) classification	NA
Material	Mxed polyolefins (B5 yarn) and HT PES
Material type and grade	Mxed polyolefins (B5 yarn) and HT PES

Physical properties

Colour	White with 3 black marking yarns
Construction	8-strand plaited rope
Density	0.99
Density [kg/m3]	0.99
Bongation [%]	18% at break
Eyes	1.8m protected eyes (PES)
Jacketed	false
Line Construction	8-strand braided
Line Linear Density (LLD)	1.015 kg/m
Line Tenacity (LT) Maximum	38.41 t/kg/m
Line Tenacity (LT) Maximum (kNg/m)	0.38 kWg/m
Line Tenacity (LT) Measured	38.09 t/kg/m
Load Bearing Linear Density (LBLD)	1.015 kg/m
Melting point	165°C
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tuck (4S-4Z)x5

Technical data

Angled Break Force (ABF) % Avg NSBF D/d = 10	181.42 (90.71)
Angled Break Force (ABF) % Avg NSBF D/d = 5	173.00 (86.50)
Angled Endurance (AE) % Avg NSBF D/d = 10	75.13
Angled Endurance (AE) % Avg NSBF D/d = 5	78.21
Average Immediate Strain (e) %LDBF:10	1.33
Average Immediate Strain (e) %LDBF:20	2.50
Average Immediate Strain (e) %LDBF:30	3.50
Average Immediate Strain (e) %LDBF:40	4.36
Average Immediate Strain (e) %LDBF:50	5.24
Axial Compression Resistance (ACR)	94.53% Avg NSBF
Line Design Break Force (LDBF)	38.7
Spliced MBL/LDBF [kN]	380
Temperature (T) % BF at 20°C -20C	107.6/133
Temperature (T) % BF at 20°C 0C	108.5/133
Temperature (T) % BF at 20°C 20C	100/124
Temperature (T) % BF at 20°C 40C	89.3/122
Temperature (T) % BF at 20°C 60C	77.5/116
Temperature (T) % BF at 20°C 80C	55/112
Unspliced MBL [kN]	423
Unspliced MBL [t]	43

Dimensions/Weight

Diameter [mm]	44
Length	220
Length [m]	220

Performance data

DNVGL	Υ
SBA	Ν
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

Approvals

Type Approved Product by DNV GL. This product is produced according to ISO 9554 and tested according to ISO 2307. Mnimum Breaking Load (MBL) is according to ISO 10556 and verified by DNV GL.

Manufactured acc. to => ISO 9554, ISO 10556 Tested acc. to => ISO 2307, CI 1500A, DNVGL-CP-0100 Type Approval No => TAK0000094

Documents

Wilhelmsen_Use and Care Timm Master 8

SDoC and MD for IHM

Related products

Is frequently bought together with 571661 METAL BRITE 25 LTR 410712 TIMM MASTER 8 44MM 110M WHITE 2X1,8M EYE 410075 TIMM MASTER 8 54MM 220M WHITE 2X1,8M EYE 410083 TIMM MASTER 8 60MM 220M WHITE 2X1,8M EYE

This page is printed from

https://www.wilhelmsen.com/product-catalogue/products/ropes/conventional-mooring-ropes/timm-master-8/timm-master-8-44mm-220m-380kn-spliced423kn-unspliced-white-2x18m-eye/