

Last updated: 08/08/2024 06:47:29

ACERA AMUNDSEN SBA 18MM 250M

Product group: **329** Product number: **L410182**



Product information

Specification

General

Invent Hazard Material (IMO/EL) classification	NA
Material type and grade	Acera H16 (HMPE)

Dimensions/Weight

Diameter [mm]	18
Length	250
Length [m]	250

Performance data

DNVGL	Y
SBA	Y
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

Physical properties

Construction	12 strand plaited
Density	0.97 (floating)
Density [kg/m ³]	0.97 (floating)
Elongation [%]	2-3% at break
Eyes	Supereye
Jacketed	false
Line Construction	12x1 braided
Line Linear Density (LLD)	0.201 kg/m
Line Tenacity (LT) Maximum	162.9 t/kg/m
Line Tenacity (LT) Maximum (kN/g/m)	1.60 kN/g/m
Line Tenacity (LT) Measured	162.3 t/kg/m
Load Bearing Linear Density (LBLD)	0.179 kg/m
Melting point	145°C - 150°C
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tension (12S/Z)x1

Technical data

Angled Break Force (ABF) % Avg NSBF D/d = 10	194.89 (97.44)
Angled Break Force (ABF) % Avg NSBF D/d = 5	188.06 (94.03)
Angled Endurance (AE) % Avg NSBF D/d = 10	98.5
Angled Endurance (AE) % Avg NSBF D/d = 5	86.85
Average Immediate Strain (e) %LDBF:10	0.37
Average Immediate Strain (e) %LDBF:20	0.64
Average Immediate Strain (e) %LDBF:30	0.87
Average Immediate Strain (e) %LDBF:40	1.09
Average Immediate Strain (e) %LDBF:50	1.30
Axial Compression Resistance (ACR)	98.95% Avg NSBF
Line Design Break Force (LDBF)	29.0
Temperature (T) % BF at 20°C -20C	115.3/115
Temperature (T) % BF at 20°C 0C	108.4/105
Temperature (T) % BF at 20°C 20C	100/100
Temperature (T) % BF at 20°C 40C	97.5/95
Temperature (T) % BF at 20°C 60C	87.23/90
Temperature (T) % BF at 20°C 80C	61.5/82
Unspliced MBL [t]	32.2

This page is printed from

<https://www.wilhelmsen.com/product-catalogue/products/ropes/high-performance-mooring-rope/acera-amundsen-sba/acera-amundsen-sba-18mm-250m/>