

Last updated: 08/08/2024 06:47:28

# ACERA DAGAMA SBA S125 [42MM/49MM] 220M

Product group: **329** Product number: **411198**



## Product information

## Specification

## General

Material type and grade	Acera H16 (HMPE), HT PES
-------------------------	--------------------------

## Dimensions/Weight

Diameter [mm]	42
Length	220
Length [m]	220

## Performance data

DNVGL	Y
SBA	Y
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

## Documents

[Wilhelmsen\\_Use and Care Acera daGama SBA](#)

## Physical properties

Jacketed	true
Line Construction	12x1 braided core (braided cover)
Line Linear Density (LLD)	1.347 kg/m
Line Tenacity (LT) Maximum	162.9 t/kg/m
Line Tenacity (LT) Maximum (kN/g/m)	1.60 kN/g/m
Line Tenacity (LT) Measured	151.2 t/kg/m
Load Bearing Linear Density (LBLD)	0.852 kg/m
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tension (12S/Z)x1

## Technical data

Angled Break Force (ABF) % Avg NSBF D/d = 10	193.77 (96.89)
Angled Break Force (ABF) % Avg NSBF D/d = 5	196.77 (98.39)
Angled Endurance (AE) % Avg NSBF D/d = 10	97.75
Angled Endurance (AE) % Avg NSBF D/d = 5	101.30
Average Immediate Strain (e) %LDBF:10	0.4
Average Immediate Strain (e) %LDBF:20	0.67
Average Immediate Strain (e) %LDBF:30	0.9
Average Immediate Strain (e) %LDBF:40	1.1
Average Immediate Strain (e) %LDBF:50	1.32
Axial Compression Resistance (ACR)	118.27% Avg NSBF
LDBF [kN] (from)	1059
LDBF [kN] (up to)	1274
LDBF [t] (from)	107.9
LDBF [t] (up to)	129.9
Line Design Break Force (LDBF)	129.9
Temperature (T) % BF at 20°C -20C	115.3/109/128
Temperature (T) % BF at 20°C 0C	108.4/109/118
Temperature (T) % BF at 20°C 20C	100/100/113
Temperature (T) % BF at 20°C 40C	97.5/98/108
Temperature (T) % BF at 20°C 60C	87.23/92/103
Temperature (T) % BF at 20°C 80C	61.5/88/95
Unspliced MBL [t]	144.1

This page is printed from

<https://www.wilhelmsen.com/product-catalogue/products/ropes/high-performance-mooring-rope/acera-dagama-sba/acera-dagama-sba-s125-42mm49mm-220m>