

Last updated: 08/08/2024 06:06:27

ACERA DAGAMA SBA S45 [24MM/27MM] 150M

Product group: 329 Product number: L410523

Product information

Specification

General

Material type and grade	Acera H16 (HMPE), HT PES
-------------------------	--------------------------

Physical properties

Jacketed	true
Line Construction	12x1 braided core (braided cover)
Line Linear Density (LLD)	0.219 kg/m
Line Tenacity (LT) Maximum	162.9 t/kg/m
Line Tenacity (LT) Maximum (kN/g/m)	1.60 kN/g/m
Line Tenacity (LT) Measured	0.1701 t/kg/m
Load Bearing Linear Density (LBLD)	0.123 kg/m
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tension (12S/Z)x1

Dimensions/Weight

Diameter [mm]	24
Length	150
Length [m]	150

Technical data

Angled Break Force (ABF) % Avg NSBF D/d = 10	193.77 (96.89)
Angled Break Force (ABF) % Avg NSBF D/d = 5	196.77 (98.39)
Angled Endurance (AE) % Avg NSBF D/d = 10	97.75
Angled Endurance (AE) % Avg NSBF D/d = 5	101.30
Average Immediate Strain (e) %LDBF:10	0.4
Average Immediate Strain (e) %LDBF:20	0.67
Average Immediate Strain (e) %LDBF:30	0.9
Average Immediate Strain (e) %LDBF:40	1.1
Average Immediate Strain (e) %LDBF:50	1.32
Axial Compression Resistance (ACR)	118.27% Avg NSBF
LDBF [kN] (from)	230
LDBF [kN] (up to)	405
LDBF [t] (from)	23.08
LDBF [t] (up to)	40.64
Line Design Break Force (LDBF)	40.64
Temperature (T) % BF at 20°C -20C	115.3/109/119
Temperature (T) % BF at 20°C 0C	108.4/109/109
Temperature (T) % BF at 20°C 20C	100/100/104
Temperature (T) % BF at 20°C 40C	97.5/98/99
Temperature (T) % BF at 20°C 60C	87.23/92/94
Temperature (T) % BF at 20°C 80C	61.5/88/86
Unspliced MBL [t]	45.08

Performance data

DNVGL	N
SBA	N
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

This page is printed from

<https://www.wilhelmsen.com/product-catalogue/products/ropes/high-performance-mooring-rope/acera-dagama-sba/acera-dagama-sba-s45-24mm27mm-150m/>