

Last updated: 04/07/2024 06:26:45

ACERA DAGAMA SBA S60 [27MM/32MM] 220M

Product group: **329** Product number: **411182**

Product information

Specification

General

Material type and grade	Acera H16 (HMPE), HT PES
-------------------------	--------------------------

Physical properties

Jacketed	true
Line Construction	12x1 braided core (braided cover)
Line Linear Density (LLD)	0.636 kg/m
Line Tenacity (LT) Maximum	162.9 t/kg/m
Line Tenacity (LT) Maximum (kN/g/m)	1.60 kN/g/m
Line Tenacity (LT) Measured	157.4 t/kg/m
Load Bearing Linear Density (LBLD)	0.375 kg/m
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tension (12S/Z)x1
X - Line Linear Density (LLD)	0.636 kg/m
X - Line Tenacity (LT) Maximum	162.9 t/kg/m
X - Line Tenacity (LT) Maximum (kN/g/m)	1.60 kN/g/m
X - Line Tenacity (LT) Measured	157.4 t/kg/m
X - Load Bearing Linear Density (LBLD)	0.375 kg/m
X - Splice type and design	Tension (12S/Z)x1

Dimensions/Weight

Diameter [mm]	27
Length	220
Length [m]	220

Technical data

Angled Break Force (ABF) %Avg NSBF D/d = 10	199.18 (99.59)
Angled Break Force (ABF) %Avg NSBF D/d = 5	184.68 (92.34)
Angled Endurance (AE) %Avg NSBF D/d = 10	86,00
Angled Endurance (AE) %Avg NSBF D/d = 5	60,04
Average Immediate Strain (e) %LDBF:10	0.20
Average Immediate Strain (e) %LDBF:20	0.42
Average Immediate Strain (e) %LDBF:30	0.62
Average Immediate Strain (e) %LDBF:40	0.82
Average Immediate Strain (e) %LDBF:50	1.01
Axial Compression Resistance (ACR)	93.16% Avg NSBF
LDBF [kN] (from)	506
LDBF [kN] (up to)	590
LDBF [t] (from)	51.5
LDBF [t] (up to)	60.2
Line Design Break Force (LDBF)	60.2
Temperature (T) %BF at 20°C -20C	111
Temperature (T) %BF at 20°C 0C	110
Temperature (T) %BF at 20°C 20C	100
Temperature (T) %BF at 20°C 40C	94
Temperature (T) %BF at 20°C 60C	86
Temperature (T) %BF at 20°C 80C	57
Unspliced MBL [t]	66.8
X - Angled Break Force (ABF) %Avg NSBF D/d = 10	199.18 (99.59)
X - Angled Break Force (ABF) %Avg NSBF D/d = 5	184.68 (92.34)
X - Angled Endurance (AE) %Avg NSBF D/d = 10	86,00
X - Angled Endurance (AE) %Avg NSBF D/d = 5	60,04
X - Average Immediate Strain (e) %LDBF:10	0.20
X - Average Immediate Strain (e) %LDBF:20	0.42
X - Average Immediate Strain (e) %LDBF:30	0.62
X - Average Immediate Strain (e) %LDBF:40	0.82
X - Average Immediate Strain (e) %LDBF:50	1.01
X - Axial Compression Resistance (ACR)	93.16% Avg NSBF
X - LDBF [kN] (from)	506
X - LDBF [kN] (up to)	590
X - LDBF [t] (from)	51.5
X - LDBF [t] (up to)	60.2
X - Line Design Break Force (LDBF)	60.2
X - Temperature (T) %BF at 20°C -20C	111
X - Temperature (T) %BF at 20°C 0C	110
X - Temperature (T) %BF at 20°C 20C	100
X - Temperature (T) %BF at 20°C 40C	94
X - Temperature (T) %BF at 20°C 60C	86
X - Temperature (T) %BF at 20°C 80C	57
X - Unspliced MBL [t]	66.8

X - LDBF [kN] (from)	500
X - LDBF [kN] (up to)	590
X - LDBF [t] (from)	51.5
X - LDBF [t] (up to)	60.2
X - Line Design Break Force (LDBF)	60.2
X - Temperature (T) % BF at 20°C -20C	111
X - Temperature (T) % BF at 20°C 0C	110
X - Temperature (T) % BF at 20°C 20C	100
X - Temperature (T) % BF at 20°C 40C	94
X - Temperature (T) % BF at 20°C 60C	86
X - Temperature (T) % BF at 20°C 80C	57
X - Unspliced MBL [t]	66.8

Performance data

DNVGL	Y
SBA	Y
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

Documents

Wilhelmsen Use and Care Acera daGama SBA