

Last updated: 04/07/2024 06:26:43

# TIMM FLEX 8 98MM 11M 2x1,8M EYE

Product group: **325**    Product number: **412784**



## Product information

## Specification

## General

Invent Hazard Material (IMO/EL) classification	NA
Material	Nylon
Material type and grade	PA 6 (Nylon)

## Dimensions/Weight

Diameter [mm]	98
Length	11
Length [m]	11

## Physical properties

Colour	White
Construction	8-strand plaited
Density	Approx. 1.14
Density [kg/m <sup>3</sup> ]	Approx. 1.14
Elongation [%]	40% at break
Jacketed	false
Line Construction	8-strand braided
Line Linear Density (LLD)	5.982 kg/m
Line Tenacity (LT) Maximum	33.23 t/kg/m
Line Tenacity (LT) Maximum (kN/g/m)	0.32 kN/g/m
Line Tenacity (LT) Measured	29.08 t/kg/m
Load Bearing Linear Density (LBLD)	5.982 kg/m
Melting point	250 °C
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tuck (4S-4Z)x5
X - Line Linear Density (LLD)	5.982 kg/m
X - Line Tenacity (LT) Maximum	33.23 t/kg/m
X - Line Tenacity (LT) Maximum (kN/g/m)	0.32 kN/g/m
X - Line Tenacity (LT) Measured	29.08 t/kg/m
X - Load Bearing Linear Density (LBLD)	5.982 kg/m
X - Splice type and design	Tuck (4S-4Z)x5

## Technical data

Average Immediate Strain (e) %\LDBF:10	8,89
Average Immediate Strain (e) %\LDBF:20	15,74
Average Immediate Strain (e) %\LDBF:30	11,67
Average Immediate Strain (e) %\LDBF:40	17,68
Average Immediate Strain (e) %\LDBF:50	18,96
Dynamic stiffness (K <sub>ex</sub> ) Exposed	11.38xTDBF
Dynamic stiffness (K <sub>sh</sub> ) Sheltered	3.00xTDBF
Line Design Break Force (LDBF)	174
Spliced MBL DRY [kN]	2001
Spliced MBL DRY [t]	204
Spliced MBL/LDBF [kN]	1706
Tail Design Break Force (TDBF)	174
Tension-tension endurance CTF 20%	3.46x10 <sup>6</sup> cycles
Tension-tension endurance CTF 50%	1.16x10 <sup>4</sup> cycles
Unspliced MBL [kN]	1895
Unspliced MBL [t]	193.3
X - Average Immediate Strain (e) %\LDBF:10	8,89
X - Average Immediate Strain (e) %\LDBF:20	15,74
X - Average Immediate Strain (e) %\LDBF:30	11,67
X - Average Immediate Strain (e) %\LDBF:40	17,68
X - Average Immediate Strain (e) %\LDBF:50	18,96
X - Dynamic stiffness (K <sub>ex</sub> ) Exposed	11.38xTDBF
X - Dynamic stiffness (K <sub>sh</sub> ) Sheltered	3.00xTDBF
X - Line Design Break Force (LDBF)	174
X - Spliced MBL DRY [kN]	2001
X - Spliced MBL DRY [t]	204
X - Spliced MBL/LDBF [kN]	1706
X - Tension-tension endurance CTF 20%	3.46x10 <sup>6</sup> cycles

X - Tension-tension endurance CTF 50%	1.16x10 <sup>4</sup> cycles
X - Unspliced MBL [kN]	2001
X - Unspliced MBL [t]	193.3

Performance data

DNVGL	N
SBA	N
Strength adjustment	10%
Var Range From	125%
Var Range To	130%

This page is printed from

<https://www.wilhelmsen.com/product-catalogue/products/ropes/rope-stretchers/tirm-flex-8-tail/tirm-flex-8-98mm-11m-2x18m-eye>