



Last updated: 08/08/2024 06:47:24

# TIMM MASTER 12 SBA TAIL FT35 [45MM] 11M

Product group: **325** Product number: **L412187** 

**Product information** 

**Specification** 

#### General

Invent Hazard Material (IMO/EJ) classification	NA
Material	75% Polyolefin & 25% HT Polyester
Material type and grade	Mxed polyolefins (B5 yarn) and HT PES

## Dimensions/Weight

Diameter [mm]	45
Length	11
Length [m]	11

## Performance data

DNVGL	Υ
SBA	Υ
Strength adjustment	10%
Var Range From	125%
Var Range To	130%

#### Physical properties

Colour	Blue and white anti-twisting colors
Construction	12 strand braided
Density	0.99
Density [kg/m3]	0.99
Bongation [%]	18% at break
Eyes	1,8m mesh braid protected eyes
Jacketed	false
Line Construction	12-strand braided
Line Linear Density (LLD)	1.102kg/m
Line Tenacity (LT) Maximum	38.41 t/kg/m
Line Tenacity (LT) Maximum (kNg/m)	0.38 kN/g/m
Line Tenacity (LT) Measured	38.12 t/kg/m
Load Bearing Linear Density (LBLD)	1.062 kg/m
Melting point	165°C
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	TM12 2G

### Technical data

Angled Break Force (ABF) % Avg NSBF D/d = 10	181.42 (90.71)
Angled Break Force (ABF) % Avg NSBF D/d = 5	173.00 (86.50)
Angled Endurance (AE) % Avg NSBF D/d = 10	78.21
Angled Endurance (AE) % Avg NSBF D/d = 5	75.13
Average Immediate Strain (e) %LDBF:10	1.09
Average Immediate Strain (e) %LDBF:20	2.26
Average Immediate Strain (e) %LDBF:30	3.36
Average Immediate Strain (e) %LDBF:40	4.38
Average Immediate Strain (e) %LDBF:50	5.35
Axial Compression Resistance (ACR)	94.53% Avg NSBF
Dynamic stiffness (Kex) Exposed	22.986xTDBF
Dynamic stiffness (Ksh) Sheltered	18.031xTDBF
LDBF [kN] (from)	316
LDBF [kN] (up to)	397
LDBF[t] (from)	32.2
LDBF[t] (up to)	40.5
Line Design Break Force (LDBF)	40.5
Temperature (T) % BF at 20°C -20C	135/101
Temperature (T) % BF at 20°C 0C	124/103
Temperature (T) % BF at 20°C 20C	100/100
Temperature (T) % BF at 20°C 40C	84/93
Temperature (T) % BF at 20°C 60C	72/89
Temperature (T) % BF at 20°C 80C	57/89
Tension-tension endurance CTF 20%	19934162223361
Tension-tension endurance CTF 50%	205233732
Unspliced MBL [t]	45.1

This page is printed from

https://www.wilhelmsen.com/product-catalogue/products/ropes/rope-stretchers/timm-master-12-sba-tail/