

Last updated: 04/07/2024 06:26:40

TIMM MASTER 12 SBA TAIL FT90 [71MM] 11M

Product group: 325 Product number: 411252



Product information

Our best selling mooring tail made from the Timm Master rope design, sold to over 6 000 vessels. Made of HT polyester and B5 polyolefin yarns which effectively absorb shock/energy in mooring systems. Typically used with steel wire and HMPE ropes. Compared to nylon stretchers, this product remains elastic for a longer period. It performs better in wet conditions, providing equal breaking strength under wet and dry conditions.

The stretcher breaking strength is given by Tail Design Break Force TDBF as per OCIMF MEG4, equal to value of MBL spliced.

Features

- Protected eyes
- Buoyant
- High elongation

Benefits

- 15-20% lighter than PES and nylon tails
- Excellent abrasion and UV resistance
- Smooth and gripable surface
- Meets all OCIMF requirements

Specification

General

Invent Hazard Material (IMO/EU) classification	NA
Material	75% Polyolefin / 25% HT Polyester
Material type and grade	Mxed polyolefins (B5 yarn) and HT PES

Physical properties

Colour	White and blue
Construction	12-strand braided
Density	0.99
Density [kg/m3]	0.99
Elongation [%]	18% at break
Eyes	1,8m mesh braid protected eyes
Jacketed	false
Line Construction	12-strand braided
Line Linear Density (LLD)	2.715 kg/m
Line Tenacity (LT) Maximum	38.41 t/kg/m
Line Tenacity (LT) Maximum (kN/g/m)	0.38 kN/g/m
Line Tenacity (LT) Measured	111
Load Bearing Linear Density (LBLD)	2.626 kg/m
Melting point	165°C
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	TM12 2G
X - Line Linear Density (LLD)	2.715 kg/m
X - Line Tenacity (LT) Maximum	38.41 t/kg/m
X - Line Tenacity (LT) Maximum (kN/g/m)	0.38 kN/g/m
X - Line Tenacity (LT) Measured	111
X - Load Bearing Linear Density (LBLD)	2.626 kg/m
X - Splice type and design	TM12 2G

Dimensions/Weight

Diameter [mm]	71
Length	11
Length [m]	11

Technical data

Average Immediate Strain (e) %\LDBF:10	1.33
Average Immediate Strain (e) %\LDBF:20	2.50
Average Immediate Strain (e) %\LDBF:30	3.50
Average Immediate Strain (e) %\LDBF:40	4.36
Average Immediate Strain (e) %\LDBF:50	5.24
Dynamic stiffness (Kex) Exposed	20.65xTDBF
Dynamic stiffness (Ksh) Sheltered	16.14xTDBF
LDBF [kN] (from)	746
LDBF [kN] (up to)	973
LDBF [t] (from)	76.0
LDBF [t] (up to)	99.2
Line Design Break Force (LDBF)	99.2
Tension-tension endurance CTF 20%	19934162223361
Tension-tension endurance CTF 50%	205233732
Unspliced MBL [t]	110.2
X - Angled Break Force (ABF) % Avg NSBF D/d = 10	0
X - Angled Break Force (ABF) % Avg NSBF D/d = 5	0
X - Angled Endurance (AE) % Avg NSBF D/d = 10	0
X - Angled Endurance (AE) % Avg NSBF D/d = 5	0
X - Average Immediate Strain (e) %\LDBF:10	1.33
X - Average Immediate Strain (e) %\LDBF:20	2.50
X - Average Immediate Strain (e) %\LDBF:30	3.50
X - Average Immediate Strain (e) %\LDBF:40	4.36
X - Average Immediate Strain (e) %\LDBF:50	5.24
X - Axial Compression Resistance (ACR)	0
X - Dynamic stiffness (Kex) Exposed	20.65xTDBF

X - Dynamic stiffness (Kex) Exposed	20.65X LDBF
X - Dynamic stiffness (Ksh) Sheltered	16.14xTDBF
X - LDBF [kN] (from)	746
X - LDBF [kN] (up to)	973
X - LDBF [t] (from)	76.0
X - LDBF [t] (up to)	99.2
X - Line Design Break Force (LDBF)	99.2
X - Tension-tension endurance CTF 20%	19934162223361
X - Tension-tension endurance CTF 50%	205233732
X - Unspliced MBL [t]	110.2

Performance data

"Copper corrosion, DIN EN ISO 2160, 24 h/100°C"	
DNVGL	Y
SBA	Y
Strength adjustment	10%
Var Range From	125%
Var Range To	130%

Approvals

Type Approved Product by DNV GL.
This product is produced according to ISO 9554 and tested according to ISO 2307 and OCIMF MEG4. Minimum Breaking Load (MBL) is according to ISO 10556 and verified by DNV GL.

Snap Back Arrestor is a verified product by DNV GL.

Manufactured acc. to => ISO 9554, ISO 10556
Tested acc. to => ISO 2307, CI 1500A, DNVGL-CP-0100
Type Approval No => TAK0000094
X- Type Approval No => TAK0000094

Documents

Timm Master 12 SBA Tail

SDoC and MD for IHM