

Last updated: 08/08/2024 06:47:24

# TIMM MASTER 12 SBA TAIL FT90 [71MM] 22M

Product group: 325 Product number: L412086

## Product information

### Specification

#### General

Invent Hazard Material (IMO/EL) classification	NA
Material	75% Polyolefin / 25% HT Polyester
Material type and grade	Mxed polyolefins (B5 yarn) and HT PES

#### Physical properties

Colour	White and blue
Construction	12-strand braided
Density	0.99
Density [kg/m <sup>3</sup> ]	0.99
Elongation [%]	18% at break
Eyes	1,8m mesh braid protected eyes
Jacketed	false
Line Construction	12-strand braided
Line Linear Density (LLD)	2.715 kg/m
Line Tenacity (LT) Maximum	38.41 t/kg/m
Line Tenacity (LT) Maximum (kN/g/m)	0.38 kN/g/m
Line Tenacity (LT) Measured	Not requested
Load Bearing Linear Density (LBLD)	2.626 kg/m
Melting point	165°C
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	TM12.2G

#### Dimensions/Weight

Diameter [mm]	71
Length	22
Length [m]	22

#### Technical data

Average Immediate Strain (e) %LDBF:10	1.09
Average Immediate Strain (e) %LDBF:20	2.26
Average Immediate Strain (e) %LDBF:30	3.36
Average Immediate Strain (e) %LDBF:40	4.38
Average Immediate Strain (e) %LDBF:50	5.35
Dynamic stiffness (Kex) Exposed	22.986xTDBF
Dynamic stiffness (Ksh) Sheltered	18.031xTDBF
LDBF [kN] (from)	746
LDBF [kN] (up to)	973
LDBF [t] (from)	76.0
LDBF [t] (up to)	99.2
Line Design Break Force (LDBF)	99.2
Tension-tension endurance CTF 20%	19934162223361
Tension-tension endurance CTF 50%	205233732
Unspliced MBL [t]	110.2

#### Performance data

DNVGL	Y
SBA	Y
Strength adjustment	10%
Var Range From	125%
Var Range To	130%

This page is printed from

<https://www.wilhelmsen.com/product-catalogue/products/ropes/rope-stretchers/timm-master-12-sba-tail/timm-master-12-sba-tail-ft90-71mm-22m/>