

Last updated: 08/08/2024 06:47:26

TIMM MASTER 8 TAIL 96MM 22M WHITE 2X2,0M EYE

Product group: **325** Product number: **410964**

Product information

Our best selling mooring tail made from the Timm Master rope design, sold to over 6 000 vessels. Made of HT polyester and B5 polyolefin yarns which effectively absorb shock/energy in mooring systems. Typically used with steel wire and HMPE ropes. Compared to nylon stretchers, this product remains elastic for a longer period. It performs better in wet conditions, providing equal breaking strength under wet and dry conditions.

Features

- Protected eyes
- Buoyant
- High elongation

Benefits

- 15-20% lighter than PES and nylon tails
- Excellent abrasion and UV resistance
- Smooth and gripable surface
- Meets all OCIMF requirements

Specification

General

| | |
|---|--|
| Invent Hazard Material (IMO/EU) classification | NA |
| Material | 75% Polyolefin / 25% HT Polyester |
| Material type and grade | Mixed polyolefins (B5 yarn) and HT PES |

Dimensions/Weight

| | |
|----------------------|----|
| Diameter [mm] | 96 |
| Length | 22 |
| Length [m] | 22 |

Performance data

| | |
|----------------------------|------|
| DNVGL | Y |
| SBA | N |
| Strength adjustment | 10% |
| Var Range From | 125% |
| Var Range To | 130% |

Approvals

Type Approved Product by DNV GL.

This product is produced according to ISO 9554 and tested according to ISO 2307. Minimum Breaking Load (MBL) is according to ISO 10556 and verified by DNV GL.

Manufactured acc. to => ISO 9554, ISO 10556

Tested acc. to => ISO 2307, CI 1500A, DNVGL-CP-0100

Type Approval No => TAK0000094

Physical properties

| | |
|--|----------------------------------|
| Colour | White with 3 black marking yarns |
| Construction | 8-strand plaited |
| Density | 0.99 |
| Density [kg/m³] | 0.99 |
| Eyes | 1,8mmesh braid protected eyes |
| Jacketed | false |
| Line Construction | 8-strand braided |
| Line Linear Density (LLD) | 4.778 kg/m |
| Line Tenacity (LT) Maximum | 38.41 t/kg/m |
| Line Tenacity (LT) Maximum (kN/g/m) | 0.38 kN/g/m |
| Line Tenacity (LT) Measured | 37.58 t/kg/m |
| Load Bearing Linear Density (LBLD) | 4.778 kg/m |
| Melting point | 165°C |
| NSBF (if requested) | Not requested |
| Rotating | false |
| Splice type and design | Tuck (4S-4Z)x5 |

Technical data

| | |
|---|--------------|
| Average Immediate Strain (e) %\LDBF:10 | 1.24 |
| Average Immediate Strain (e) %\LDBF:20 | 2.50 |
| Average Immediate Strain (e) %\LDBF:30 | 3.71 |
| Average Immediate Strain (e) %\LDBF:40 | 4.82 |
| Average Immediate Strain (e) %\LDBF:50 | 5.88 |
| Dynamic stiffness (Kex) Exposed | 18.896xTDBF |
| Dynamic stiffness (Ksh) Sheltered | 13.637xTDBF |
| Line Design Break Force (LDBF) | 180 |
| Spliced MBL DRY [t] | 180 |
| Spliced MBL/LDBF [kN] | 1761 |
| Tension-tension endurance CTF 20% | 2675208408,5 |
| Tension-tension endurance CTF 50% | 701711 |
| Unspliced MBL [kN] | 199 |
| Unspliced MBL [t] | 199.5 |

Documents

[SDoC and MD for IHM](#)

[Timm Master Tail - Use and Care Manual](#)

This page is printed from

<https://www.wilhelmsen.com/product-catalogue/products/ropes/rope-stretchers/timm-master-8-tail/timm-master-8-tail-96mm-22m-1761kn-spliced-white-2x20m-eye/>