

# KLÜBERPLEX BEM 41-132 25 KG

Product group: **686** Product number: **210064**

KLÜBERPLEX BEM 41-132 is a high-temperature, long-term grease for rolling bearings. Supported by a wide operating temperature range, it comes with excellent oxidation, wear and corrosion resistance, keeping your bearings well-protected and easy to maintain.



## Product information

Rolling bearings are prone to damage when there is consistent friction and chafing. In less severe cases, your bearings may suffer simple scratches and surface roughening. But in more costly ones, complete bearing failure occurs. Thereupon, KLÜBERPLEX BEM41-132 was developed with synthetic hydrocarbon oil, mineral oil and a special lithium soap, formulated to safeguard your rolling bearings from such damage - and keep them running safely and reliably for you.

KLÜBERPLEX BEM41-132 includes special additives that offer it excellent oxidation resistance, protecting from degradation that oxidation brings about. Moreover, these select ingredients also serve to defend your rolling bearings against wear and corrosion. Expect to enjoy longer service lives of your parts and reduced maintenance costs for you.

Since the operating temperature of your rolling bearings is subject to both internal friction and external environmental conditions, the ideal lubricant is also one that is versatile and adept at handling a wide range of temperatures. KLÜBERPLEX BEM41-132 is supported with a wide operating temperature range and is suitable for high-temperature applications.

### Features

- Good high-temperature behaviour
- Oxidation resistance
- Wear and corrosion protection
- Optimised oil release
- Long-term lubricant

### Benefits

- Protects your rolling bearings from damage by oxidation
- Protects your rolling bearings from corrosion
- Protects your rolling bearings from chafing and wear
- Extends service lives of your parts
- Reduces maintenance needs

## Specification

## General

Invent Hazard Material (IMO/EL) classification	C-30
--	------

## Dimensions/Weight

Packing Size	25 kg
--------------	-------

## Performance data

Corrosion inhibiting properties of lubricating greases, DIN 51802, (SKF-EMCOR), test duration: 1 week, distilled water	≤1 corrosion degree
Drop point, DIN ISO 2176, IP 396 [°C]	≥250
FAG FE9 rolling bearing tester, DIN 51821 pt. 02, speed: 6000 min <sup>-1</sup> , axial load: 1500 N, temperature: 150 °C, service life F50 [h]	≥100
Low-temperature torque, IP 186, -40 °C, running [mNm]	≤200
Low-temperature torque, IP 186, -40 °C, start [mNm]	≤1000
Lower service temperature	-40°C / - 40°F
Oil separation, DIN 51817 N, after 7 d/40 °C	≤4% by weight
Upper service temperature	150°C / 302°F
Worked penetration, DIN ISO 2137, 25 °C, lower limit value [mm]	265 x 0.1
Worked penetration, DIN ISO 2137, 25 °C, upper limit value [mm]	295 x 0.1

## Documents

[SDoC and MD for IHM](#)

## Directions for use

KLÜBERPLEX BEM 41-132 is suitable for the long-term or lifetime lubrication of rolling bearings. You may use it for rolling bearings with a high degree of sliding friction (e.g. tapered, cylinder or spherical roller bearings) or for life-lubricated deep groove ball bearings and rolling bearings. It is also appropriate to use for rolling bearings in vehicle components.

Apply KLÜBERPLEX BEM 41-132 with a spatula, brush, or grease gun. If you would like to use an automatic lubricating system, please check the pumpability beforehand.

We also recommend that you test the compatibility of KLÜBERPLEX BEM 41-132 with the materials it will contact.

This page is printed from

<https://www.wilhelmsen.com/zh-hans/product-catalogue/products/speciality-lubricants/kluberplex-bem-41-132-25-kg>

## Physical properties

Colour	Yellow
Density at 20°C [g/cm <sup>3</sup> ]	~ 0.90
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C [mm <sup>2</sup> /s]	~ 14
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C [mm <sup>2</sup> /s]	~ 120
Lubricating greases -K, DIN 51825 in connection with DIN 51502	KFHC2N- 30L

## Technical data

Chemical composition, thickener	Special lithium soap
Chemical composition, type of oil	Synthetic hydrocarbon oil, mineral oil
Shelf life [months]	36
Speed factor (n x dm)	~ 1 000 000 mm/min